



BIANCO ASSOLUTO IMPECCABILE

Bianco Assoluto Impeccabile: a pure, esteemed and classy marble coming from Asia. Thanks to its durability and excelent strenght, it is suitable for interior design. The polished and honed finishes enhance the beauty of this marble. Thanks, also, to its hardness and waterproofness, it is suitable for any exterior design.

Zagross Marmi is a leading company and exclusive authorized distributor of BIANCO ASSOLUTO IMPECCABILE. 30 years of experience in this field makes the Zagross Marmi leader in the marble market, always looking for unique materials, from Rosa Bellissimo to the current exclusivity of Bianco Assoluto Impeccabile for the whole Italy.

TECHNICAL SHEET

| Test* | | Test Values^ | |
|---|-------------------------|--|-------------|
| Chemical Analysis (Unit % by mass) | | Protocol – i)ASTM C-25 ii) AAA &ICP -OES | |
| Loss of Ignition (at 1000° ± 10° C) | | 43.7 | |
| Silica (as SiO ₂) | | 0.22 | |
| Alumina (as Al ₂ O ₃) | | 0.02 | |
| Iron Oxide (as Fe ₂ O ₃) | | 0.02 | |
| Lime (as CaO) | | 55.5 | |
| Magnesia (as MgO) | | 0.27 | |
| Titania (as TiO ₂) | | Nil | |
| Soda (as Na ₂ O) | | Less than 0.01 | |
| Potash (as K ₂ O) | | Less than 0.01 | |
| Calcium Carbonate (as CaCo₃) | | 99.07 | |
| Physical Analysis | | | |
| Test* | | Test Values^ | Protocol |
| Mohs Hardness | 3 | | Moh's Scale |
| Water Absorption (% by wt) | Less than 0.1 | | ASTM C-97 |
| Bulk Specific Gravity | 2.71 | | ASTM C-97 |
| Compressive Strength (kg/cm²) | Dry - 559 Wet - 480 | | ASTM C-170 |
| Flexural Strength (MPa) | Dry - 10.95 Wet - 11.44 | | ASM C- 880 |



+ 99,07 % calcium carbonate



- 0.1 % water absorption



-0,01% iron oxide

OUR LOCATIONS

S.P Comiso-Chiaramonte Gulfi, C/da Cifali Km 3.750 97012 Chiaramonte Gulfi (RG), Italy Tel +39 0932 929028

