



## BIANCO ASSOLUTO IMPECCABILE

Bianco Assoluto Impeccabile: a pure, esteemed and classy marble coming from Asia. Thanks to its durability and excellent strength, it is suitable for interior design. The polished and honed finishes enhance the beauty of this marble. Thanks, also, to its hardness and waterproofness, it is suitable for any exterior design.

Zagross Marmi is a leading company and exclusive authorized distributor of BIANCO ASSOLUTO IMPECCABILE.

30 years of experience in this field makes the Zagross Marmi leader in the marble market, always looking for unique materials, from Rosa Bellissimo to the current exclusivity of Bianco Assoluto Impeccabile for the whole Italy.

## TECHNICAL SHEET

Test*	Test Values <sup>^</sup>	
<b>Chemical Analysis (Unit % by mass)</b>	<b>Protocol – i)ASTM C-25 ii) AAA &amp; ICP -OES</b>	
Loss of Ignition (at 1000° ± 10° C)	43.7	
Silica (as SiO <sub>2</sub> )	0.22	
Alumina (as Al <sub>2</sub> O <sub>3</sub> )	0.02	
Iron Oxide (as Fe <sub>2</sub> O <sub>3</sub> )	0.02	
Lime (as CaO)	55.5	
Magnesia (as MgO)	0.27	
Titania (as TiO <sub>2</sub> )	Nil	
Soda (as Na <sub>2</sub> O)	Less than 0.01	
Potash (as K <sub>2</sub> O)	Less than 0.01	
Calcium Carbonate (as CaCO <sub>3</sub> )	99.07	
<b>Physical Analysis</b>		
Test*	Test Values <sup>^</sup>	Protocol
Mohs Hardness	3	Moh's Scale
Water Absorption (% by wt)	Less than 0.1	ASTM C-97
Bulk Specific Gravity	2.71	ASTM C-97
Compressive Strength (kg/cm <sup>2</sup> )	Dry - 559 Wet - 480	ASTM C-170
Flexural Strength (MPa)	Dry - 10.95 Wet - 11.44	ASM C- 880



+ 99,07 %  
calcium carbonate



- 0,1 %  
water absorption



- 0,01 %  
iron oxide

## OUR LOCATIONS

S.P Comiso-Chiaramonte Gulfi, C/da Cifali Km 3.750  
97012 Chiaramonte Gulfi (RG), Italy  
Tel +39 0932 929028

zagrossmarmi.com



Via Argine Carrione 7  
540335 Carrara (MS), Italy  
Tel +39 0585 1610888